

### **Amendments to the Specification**

The specification is amended as follows:

The original languages shown at page 5, lines 21-24 is replaced with the following replacement languages: After the pattern forming process S200 has been completed, the mesh forming process S300 for transferring the predetermined mesh onto the entire etching area of the mold using the spraying method will be performed. Under the spraying method, a liquid which can resist the etching chemicals, for example an acid-resistant substance, is sprayed onto the mold where the pattern forming process has been carried out. By the spraying of the liquid, the mold has a mesh pattern of the liquid. The mesh pattern is a state that the particles of the liquid is scattered on the surface of the mold by spraying. The mesh forming process is basically performed to express the texture of wood on the door.